

Solda-Met™ 40L

Tin-Lead Soft Solder

Solda-Met™40L has a wide melting range and is widely used in soldering copper and copper based alloys.

Standard	ISO 9453:2014	Alloy No. 114
Melting Range	183°C - 235°C	
Chemical Composition	Tin Lead	40% 60%
Conditions for Use	For use with a separate flux, Solda-Met 1C, 2C, 3C or with a flux core	
Physical Properties	Density - 9.31 g/cm ³	
Forms of Supply	Available as solid wire or with a flux core of either rosin or acid fluxes	

